Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China
Contact: +86-18678775281 Website: www.china-polymer.com

Product name: PGA

CAS: 26124-68-5



Item	Standard	Inspection method (equipment)
Appearance	Yellow to light brown solid	Visual inspection
Melting point	220-240℃	Differential Scanning Calorimetry (DSC)
Moisture	＜0.5%	Quick Moisture Analyzer
Ignition residue	≤0.5%	Ignition residue test
Total heavy metal content (Pb)	≤10ppm	Heavy Metal Inspection Act
Acid value	＞6.5	Simulated body fluid (pH=7.4) soaking sample The product was extracted in a constant temperature shaking table at 37℃ for 24h
Melting index (mfr)	＜30.0g/10min	Melt flow rate meter

(The above table is our reference indicator)

Unilong Industry