Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China
Contact: +86-18678775281 Website: www.china-polymer.com

Product name: PLGA

CAS: 26780-50-7



Item	Standard
Appearance	White to light yellow solid
Viscosity	2.8-3.2dL/g
Glass transition temperature	40-60°C
Water	≤0.5%
Ignition residue	≤0.2%
Total content of heavy metals	≤10ppm
Density	1.20- 1.30g/cm3
Specific rotation	- 10 o~ +10o
Acidity	5.0-7.0

(The above table is our reference indicator)

Unilong Industry